



# Hygard® BR1250 sheet

## Ballistic glazing - Level 3

Hygard® BR1250 ballistic grade sheet is a 1.250", 4-ply polycarbonate laminate that meets UL 752 Level 3 rating for .44 Magnum ballistic attack, HP White TP 0500 Level IV, and ASTM F 1233 Class 5. Unlike glass-clad products, this all-polycarbonate laminate resists spalling and white-out after repeated high force and ballistic impacts, an advantage in maintaining visibility of a threat during an attack. All Hygard products incorporate Makrolon® polycarbonate sheet produced for high optical quality in security glazing laminates. Exterior surfaces have a proprietary Makrolon AR hardcoat that facilitates cleaning and resists marring, chemical, and graffiti attack. Applications include security doors, windows, and other areas that require these specific levels of protection. Hygard BR1250 sheet has a seven (7) year Limited Product Warranty against coating failure, yellowing, and hazing. The terms of the warranty are available upon request.

## Applications


Government and detention facilities, banks, heavy equipment glazing, specialty retailers, 24 hour convenience stores, cash transaction windows

Typical Properties*	
Property	Values
Gauge / Tolerance	1.30 in ± 5%
Weight	8.1 lbs / sq ft
Shading Coefficient	0.81
U-Value	0.51
Light Transmission	72%

\*Typical properties are not intended for specification purposes

Product Performance Ratings
<p><b>BALLISTIC</b>            UL 752 Level 3 (.44 Magnum lead semi-wadcutter gas checked)            NIJ Level II, Level IIIA</p>
<p><b>FORCED ENTRY &amp; CONTAINMENT</b>            ASTM F 1233.08 Class 5 Body Passage            ASTM F 1233.08 Class 2.5 Contraband Passage            ASTM F 1915.03 Grade 1            H.P. White TP 0500.03 Level IV Sequence 43-44</p>
<p><b>AGENCY INFORMATION</b>            UL File: BP6864            Combustibility Class CC1            Miami-Dade NOA 12-00605.05            ICC-ES ESR-2728</p>

## Hygard® BR1250 Sheet Construction



# Hygard® BR1250 sheet

## Glazing recommendations

- Structural security framing systems with equal or greater forced entry and/or ballistics ratings as the selected Hygard laminate are recommended
- Hygard laminate should be cut to allow for a minimum of one (1) inch edge engagement in the frame, with sufficient rabbet depth for material expansion (approx. 1/16"/ft.)
- Use wet or dry sealants/gaskets that are compatible with polycarbonate
- Remove protective masking after glazing operations are completed and before prolonged exposure to direct sunlight, moisture, or high temperature

## Standard sheet size

48" x 60", 48" x 72", 38" x 78", 38" x 96", 48" x 96", 60" x 72", 60" x 96"

## Product specification

Hygard BR1250 polycarbonate laminate:

- Four-ply, clear Makrolon® polycarbonate sheet constructed as follows:
  - 1/8" Makrolon AR-1 abrasion resistant surface
  - Polyurethane bonding interlayer
  - 1/2" Makrolon polycarbonate sheet
  - Polyurethane bonding interlayer
  - 1/2" Makrolon polycarbonate sheet
  - Polyurethane bonding interlayer
  - 1/8" Makrolon AR-1 abrasion resistant surface

Distributed by:



**Piedmont Plastics®**  
where solutions take shape

Toll Free: 1.800.277.7898

[www.piedmontplastics.com](http://www.piedmontplastics.com)



The manner in which you use and the purpose to which you put and utilize our products, technical assistance and information (whether verbal, written or by way of production evaluations), including any suggested formulations and recommendations, are beyond our control. Therefore, it is imperative that you test our products, technical assistance, information and recommendations to determine to your own satisfaction whether our products, technical assistance and information are suitable for your intended uses and applications. This application-specific analysis must at least include testing to determine suitability from a technical as well as health, safety, and environmental standpoint. Such testing has not necessarily been done by Covestro.

Unless we otherwise agree in writing, all products are sold strictly pursuant to the terms of our standard conditions of sale which are available upon request. All information and technical assistance is given without warranty or guarantee and is subject to change without notice. It is expressly understood and agreed that you assume and hereby expressly release us from all liability, in tort, contract or otherwise, incurred in connection with the use of our products, technical assistance, and information. Any statement or recommendation not contained herein is unauthorized and shall not bind us. Nothing herein shall be construed as a recommendation to use any product in conflict with any claim of any patent relative to any material or its use. No license is implied or in fact granted under the claims of any patent.

With respect to health, safety and environment precautions, the relevant Material Safety Data Sheets (MSDS) and product labels must be observed prior to working with our products.