



# Technical Data Sheet

## Harkness Industries MP 700

### Polyurethane Composition

MP 700 is a high performance polyester based urethane. This polyurethane is formulated to give an excellent balance of properties for a wide variety of applications including springs, scraper blades, die cutting pads, bumpers, chute liners, wheels, tires, and many more.

### Physical Properties

Shore A Hardness .....	70 +/- 5
100% Modulus, psi (Mpa) .....	310 (2.2)
300% Modulus, psi (Mpa) .....	850 (5.8)
Tensile, psi (Mpa) .....	4800 (32.8)
Elongation, % .....	500%
Tear Strength, Split (ASTM D-470) pli, (kN/m) .....	55 (9.5)
Tear Strength, Die C (ASTM D-624) pli, (kN/m) .....	240 (41.8)
Tear Strength, Die B (ASTM D-624) pli, (kN/m) .....	215 (37.6)
Compression Set % .....	12
22 hours @ 158°F (70°C), Method B	
Bell Brittle Point, °F (°C) .....	- 70 (-57)
Tabor Abrasion, H-18 100 gm Load	
Average Loss / 1000 cycles, grams .....	0.040
Specific Gravity .....	1.26



Distributed by:



**Piedmont Plastics**<sup>®</sup>  
where solutions take shape

Toll Free: 1.800.277.7898  
[www.piedmontplastics.com](http://www.piedmontplastics.com)