



Bayblend® MTR AG sheet

Mass transportation rail anti-graffiti low FST

Bayblend® MTR AG sheet is a high performance product extension of Bayblend MTR sheet providing increased resistance to graffiti, scratches, cleaning chemicals, and foodstuff stains. This opaque flame retardant polycarbonate based sheet offers a unique combination of flammability characteristics, robust mechanical properties, and ease of fabrication. Bayblend MTR AG complies with the flammability and smoke emission requirements for transit materials per the U.S. Federal Railroad Administration, listed in DOT: 49 CFR 238, and meets the criteria in the Bombardier Transportation Standard SMP 800-C for Toxic Gas Generation.

Bayblend MTR AG has a lower specific gravity, higher stiffness, higher strength, and greater toughness than typical non-metallic materials used for mass transportation interior components. This combination of physical properties allows for design of thinner and lighter parts that often do not require secondary reinforcement or stiffeners in the application. Bayblend MTR AG is available in a variety of textures and colors or custom printed decoration.

Applications

Thermoformed rail interior parts, such as seating components, wall cladding, window reveals, and ceiling panels

Typical Properties*			
Property	Test Method	Units	Values
PHYSICAL			
Specific Gravity	ASTM D 792	–	1.3
Moisture Absorption, Equilibrium, 24 hours	ASTM D 570	%	0.1
MECHANICAL			
Tensile Strength, Yield	ASTM D 638	psi	8,400
Tensile Elongation	ASTM D 638	%	10
Tensile Stress at Break	ASTM D 638	psi	6,900
Modulus of Elasticity	ASTM D 638	psi	570,000
Flexural Modulus	ASTM D 790	psi	520,000
Flexural Stress	ASTM D 790	psi	15,000
Izod Impact Strength, Notched @ 0.118"	ASTM D 256	ft·lbs/in	1.5
Instrumented Impact @ 0.118"	ASTM D 3763	ft·lbs	24
Rockwell Hardness	ASTM D 785	–	M60/R116
THERMAL			
Coefficient of Thermal Expansion	ASTM D 696	in/in/°F	2.70 x 10 ⁻⁵
Heat Deflection Temperature @ 264 psi	ASTM D 648	°F	206
Heat Deflection Temperature @ 66 psi	ASTM D 648	°F	219
Vicat Softening Temperature	ASTM D 1525	°F	233
Thermal Resistance R-value	ASTM E 1530	Btu ft ² ·hr°F	0.90
Thermal Conductivity	ASTM E 1530	Btu in./ft ² ·hr°F	16.6
ELECTRICAL**			
Dielectric Constant @ 1 MHz, @ 0.118"	ASTM D 150	–	2.9
Dielectric Constant @ 60 Hz, @ 0.125"	ASTM D 150	–	3.0
Dissipation Factor @ 1 MHz, @ 0.118"	ASTM D 150	–	0.007
Dissipation Factor @ 60 Hz, @ 0.125"	ASTM D 150	–	0.004
Dielectric Strength	ASTM D 149	V/mil	659
Volume Resistivity @ 0.112"	ASTM D 257	Ohm·cm	4.0 x 10 ¹⁵
Volume Resistivity @ 0.125"	ASTM D 257	Ohm·cm	6.6 x 10 ¹⁵
FLAMMABILITY			
Flame Spread Index	ASTM E 162	Is (1.5 min)	<35
Burning Dripping	ASTM E 162	–	None
Smoke Density	ASTM D 662	Ds (1.5 min)	<100
Smoke Density	ASTM E 662	Ds (4.0 min)	<200
Bombardier Toxic Gas Generation	SMP 800-C	–	Pass
Boeing Toxic Gas Generation	BSS 7239	–	Pass

*Typical Properties are not intended for specification purposes


** Some electrical properties are for the base MTR sheet

Bayblend® MTR AG sheet

Weight savings

Bayblend® MTR AG has a lower specific gravity and higher stiffness than typical non-metallic materials used for mass transportation interior components. This unique property profile can provide over 30% weight savings for components designed for specific stiffness when compared with other materials as shown below.

Specific Gravity of Competitive Materials



Thermoforming

Bayblend MTR AG can be thermoformed using conventional tooling and processes for thermoplastic materials such as PVC alloys, ABS, and polycarbonate. Optimal results can be obtained with fluid-heated aluminum tooling. Suggested tooling temperatures are 205°F – 215°F. Depending on geometry Bayblend MTR AG parts can be formed with and without vacuum-assist and plug-assist. Textures can be achieved via in mold texturing or through retention of texture as supplied using vacuum-forming. Recommended sheet temperature for thermoforming is 320°F – 340°F. For best results, Bayblend MTR AG should be pre-dried in a desiccated hot-air circulating oven at 180°F – 200°F from 8 to 24 hours depending upon sheet thickness. Prior to placing an order for Bayblend product or designing tooling, Bayer recommends thermoforming Bayblend sample material in a tool that represents the actual part or approximates the desired part geometry to determine optimal forming conditions and assessing part quality.

Secondary operations

Bayblend MTR AG can be cut and drilled with standard saws and tooling. Finished parts can be assembled using conventional mechanical fastening techniques or by gluing or welding.

Depending on roll pattern, the darker the color the more the sheet can be prone to exhibit visual inconsistencies in gloss due to limitations of pattern roll technologies.

Distributed by:



Piedmont Plastics®
where solutions take shape

Toll Free: 1.800.277.7898

www.piedmontplastics.com



The manner in which you use and the purpose to which you put and utilize our products, technical assistance and information (whether verbal, written or by way of production evaluations), including any suggested formulations and recommendations, are beyond our control. Therefore, it is imperative that you test our products, technical assistance, information and recommendations to determine to your own satisfaction whether our products, technical assistance and information are suitable for your intended uses and applications. This application-specific analysis must at least include testing to determine suitability from a technical as well as health, safety, and environmental standpoint. Such testing has not necessarily been done by Covestro.

Unless we otherwise agree in writing, all products are sold strictly pursuant to the terms of our standard conditions of sale which are available upon request. All information and technical assistance is given without warranty or guarantee and is subject to change without notice. It is expressly understood and agreed that you assume and hereby expressly release us from all liability, in tort, contract or otherwise, incurred in connection with the use of our products, technical assistance, and information. Any statement or recommendation not contained herein is unauthorized and shall not bind us. Nothing herein shall be construed as a recommendation to use any product in conflict with any claim of any patent relative to any material or its use. No license is implied or in fact granted under the claims of any patent.

With respect to health, safety and environment precautions, the relevant Material Safety Data Sheets (MSDS) and product labels must be observed prior to working with our products.