



Hygard® EX1300 sheet

Extreme blast resistant

Hygard® EX1300 laminates are engineered to meet U.S. Federal Government anti-terrorism force protection standards for blast resistant glazing. Glazed monolithically or as the interior lite in a dual glazed system with glass, Hygard EX1300 is suitable for commercial and government window applications requiring the highest level of transparent protection against defined high pressure loads and shock waves. These laminates are designed specifically for architectural applications that require blast mitigation performance of 45 psi or higher.

Applications

Government buildings, embassies, military buildings/facilities, chemical plants, airports, mass transit terminals, nuclear plants, power generation facilities, federal courthouse and 911 emergency centers

Additional high performance security features that can be specified include:

- Ballistic resistance
- Containment and forced entry resistance
- Hurricane and tornado protection

Typical Properties

Property	Test Method	Units	Values
PHYSICAL			
Specific Gravity	ASTM D 792	-	1.2
Chemical Resistance	ASTM D 1308	-	Pass
Poisson's Ratio*	ASTM E 132	-	0.38
OPTICAL			
Light Transmission @ 1.25"	ASTM D 1003	%	67
Haze	ASTM D 1003	%	<1
MECHANICAL			
Tensile Strength, Ultimate*	ASTM D 638	psi	9,500
Tensile Modulus*	ASTM D 638	psi	340,000
Elongation*	ASTM D 638	%	110
Flexural Strength*	ASTM D 790	psi	13,500
Taber Abrasion @ 100 Cycles, Delta Haze CS-10F Wheel @ 500 g load	ASTM D 1044	%	2
THERMAL			
Coefficient of Thermal Expansion	ASTM D 696	in/in/°F	3.75 x 10 ⁻⁵
Heat Deflection Temperature @ 264 psi	ASTM D 648	°F	270
Heat Deflection Temperature @ 66 psi	ASTM D 648	°F	280
U-Factor	NFRC 100-2010**	Btu/h-ft ² -°F	0.54
Shading Coefficient	NFRC 100-2010	-	0.90
Solar Heat Gain Coefficient	NFRC 100-2010	-	0.79
FLAMMABILITY			
Burn Rate Class	ASTM D 635	<1" extent of burn	CC-1
Ignition Temperature, Self	ASTM D 1929	°F	890
Ignition Temperature, Flash	ASTM D 1929	°F	800

*Values reported are for the Makrolon® sheet component of the laminate

**National Fenestration Rating Council

Physical Performance Data

Performance	Standard / Test Method	Protection Level
Blast Resistance 45+ psi	Exceeds GSA, DoD (UFC) DoS	Modeling / testing required
Ballistic	UL 752	Level 3
	NIJ	Level II, Level IIIA

Agency Information

ICC-ES Evaluation Report ESR-2728

Miami-Dade NOA #12-0605.05

Hygard® EX1300 sheet

Glazing recommendations

Hygard EX1300 is one component in a blast resistant window and must be modeled and tested in structural framing which is designed and approved for specified government blast pressure levels and impulses.

- Properly size material thickness based on window aspect ratio
- Glazing bite – recommend a minimum of 1-1/2"
- Rabbet depth to allow glazing bite + material thermal expansion and contraction (approx. 1/16"/ft.)
- Cut and fabricate Hygard EX1300 with approved equipment and techniques
- Utilize compatible structural sealants, gaskets, tapes, and setting blocks
- Choose an approved structural frame design rated for the appropriate blast load with an appropriate anchor type
- Conduct computer modeling on complete window design
- Mockup testing and engineering – industry standards are either shock tube or live explosives open arena testing
- Following recommended cleaning procedures per Covestro manual
- Remove protective masking
 - after the glazing operations are completed but not before other trades have completed their work and cleanup
 - before prolonged exposure to direct sunlight, moisture, and high temperatures

NOTE: Consult Covestro Makrolon Sheet Fabrication Guide for additional information

Distributed by:



Piedmont Plastics®
where solutions take shape

Toll Free: 1.800.277.7898

www.piedmontplastics.com



The manner in which you use and the purpose to which you put and utilize our products, technical assistance and information (whether verbal, written or by way of production evaluations), including any suggested formulations and recommendations, are beyond our control. Therefore, it is imperative that you test our products, technical assistance, information and recommendations to determine to your own satisfaction whether our products, technical assistance and information are suitable for your intended uses and applications. This application-specific analysis must at least include testing to determine suitability from a technical as well as health, safety, and environmental standpoint. Such testing has not necessarily been done by Covestro.

Unless we otherwise agree in writing, all products are sold strictly pursuant to the terms of our standard conditions of sale which are available upon request. All information and technical assistance is given without warranty or guarantee and is subject to change without notice. It is expressly understood and agreed that you assume and hereby expressly release us from all liability, in tort, contract or otherwise, incurred in connection with the use of our products, technical assistance, and information. Any statement or recommendation not contained herein is unauthorized and shall not bind us. Nothing herein shall be construed as a recommendation to use any product in conflict with any claim of any patent relative to any material or its use. No license is implied or in fact granted under the claims of any patent.

With respect to health, safety and environment precautions, the relevant Material Safety Data Sheets (MSDS) and product labels must be observed prior to working with our products.