



# Makrolon® DX-NR sheet

## Polycarbonate diffuser sheet for outdoor LED lighting

Makrolon DX-NR is a translucent polycarbonate product specifically designed for use as a lighting lens in outdoor applications. The diffuser technology helps to provide uniform luminance and ensures elimination of LED hot spots while maintaining high light transmission. The advanced UV resistance technology provides long lasting weathering performance and the non-reflective texture built into the UV resistant side of the sheet, enhances its aesthetics.

When compared to other light diffusing products such as glass and acrylic, Makrolon DX-NR has superior impact strength and toughness. Its higher flammability resistance and wider service temperature provide an additional advantage over acrylic diffusers.

Typical Properties*			
Property	Test Method	Units	Values
<b>PHYSICAL</b>			
Specific Gravity	ASTM D 792	-	1.2
Water Absorption, 24 hrs	ASTM D 570	%	0.15
Poisson's Ratio	ASTM E 132	-	0.38
Light Transmission @ 0.060" / 0.118"	ASTM D 1003	%	69 / 61
Light Diffusion @ 0.060" / 0.118"	FWHM	degrees	150 / 152
<b>MECHANICAL</b>			
Tensile Strength, Ultimate	ASTM D 638	psi	9,500
Tensile Strength, Yield	ASTM D 638	psi	9,000
Tensile Modulus	ASTM D 638	psi	340,000
Elongation	ASTM D 638	%	110
Flexural Strength	ASTM D 790	psi	13,500
Flexural Modulus	ASTM D 790	psi	345,000
Instrumented Impact @ 0.118"	ASTM D 3763	ft-lbs	47
<b>THERMAL</b>			
Coefficient of Thermal Expansion	ASTM D 696	in/in/°F	3.75 x 10 <sup>-5</sup>
Coefficient of Thermal Conductivity	ASTM C 177	BTU-in/hr-ft <sup>2</sup> -°F	1.35
Heat Deflection Temperature @ 264 psi	ASTM D 648	°F	270
Heat Deflection Temperature @ 66 psi	ASTM D 648	°F	280
<b>ELECTRICAL</b>			
Dielectric Constant @10 Hz	ASTM D 150	-	3.0
Dielectric Constant @ 60 Hz	ASTM D 150	-	3.2
Volume Resistivity	ASTM D 257	Ohm-cm	>8 x 10 <sup>15</sup>
<b>FLAMMABILITY</b>			
Flame Class @ 0.060"	UL 94	-	V2**
@ 0.118"	UL 94	-	HB**
Horizontal Burn	ASTM D 635	in.	<1 (CC1)
Glow Wire Flammability Index	DIN EN 60695-2-12	°F	1560
Glow Wire Ignition Test	DIN EN 60695-2-13	°F	1607

\*Typical properties are not intended for specification purposes

\*\*Test results, product not UL 94 Listed

Distributed by:



Toll Free: 1.800.277.7898  
www.piedmontplastics.com



# Makrolon® DX-NR



©Copyright, Covestro, 2015  
Makrolon® is a registered trademark of Covestro

Distributed by:



**Piedmont Plastics®**

where solutions take shape

Toll Free: 1.800.277.7898

[www.piedmontplastics.com](http://www.piedmontplastics.com)

The manner in which you use and the purpose to which you put and utilize our products, technical assistance and information (whether verbal, written or by way of production evaluations), including any suggested formulations and recommendations, are beyond our control. Therefore, it is imperative that you test our products, technical assistance, information and recommendations to determine to your own satisfaction whether our products, technical assistance and information are suitable for your intended uses and applications. This application-specific analysis must at least include testing to determine suitability from a technical as well as health, safety, and environmental standpoint. Such testing has not necessarily been done by Covestro.

Unless we otherwise agree in writing, all products are sold strictly pursuant to the terms of our standard conditions of sale which are available upon request. All information and technical assistance is given without warranty or guarantee and is subject to change without notice. It is expressly understood and agreed that you assume and hereby expressly release us from all liability, in tort, contract or otherwise, incurred in connection with the use of our products, technical assistance, and information. Any statement or recommendation not contained herein is unauthorized and shall not bind us. Nothing herein shall be construed as a recommendation to use any product in conflict with any claim of any patent relative to any material or its use. No license is implied or in fact granted under the claims of any patent.

With respect to health, safety and environment precautions, the relevant Material Safety Data Sheets (MSDS) and product labels must be observed prior to working with our products.