



Makrolon® VR sheet

Flexible Enclosure

Makrolon® VR sheet is a polycarbonate product designed for high optical quality and exceptional durability. Proprietary UV technology ensures long lasting outdoor weathering performance while protecting occupants from the sun's harmful UV rays. State-of-the-art manufacturing processes provide low optical distortion for clear views and unparalleled sight lines.

Makrolon VR can be easily cut and sewn, offering a high clarity, wrinkle-free alternative to flexible vinyl. The product can be rolled, making it ideal for applications with limited storage.

Makrolon VR is offered with a five (5) year Limited Product Warranty against breakage. The terms of the warranty are available upon request.

Applications

Marine flexible enclosures, tent and awning enclosures

Typical Properties*			
Property	Test Method	Units	Values
PHYSICAL			
Specific Gravity	ASTM D 792	-	1.2
Light Transmission, Clear @ 0.040"	ASTM D 1003	%	90
MECHANICAL			
Izod Impact Strength, Notched @ 0.125"	ASTM D 256	ft-lbs/in	16
Izod Impact Strength, Unnotched @ 0.125"	ASTM D 256	ft-lbs/in	No Break
Instrumented Impact @ 0.125"	ASTM D 3763	ft-lbs	47
Poisson's Ratio	ASTM E 132	-	0.38
Rockwell Hardness	ASTM D 785	-	M70/R118
THERMAL			
Coefficient of Thermal Expansion	ASTM D 696	in/in/°F	3.75 x 10 ⁻⁵
Heat Deflection Temperature @ 264 psi	ASTM D 648	°F	270
Heat Deflection Temperature @ 66 psi	ASTM D 648	°F	280

*Typical properties are not intended for specification purposes

Distributed by:



Piedmont Plastics®
where solutions take shape


Toll Free: 1.800.277.7898
www.piedmontplastics.com



Makrolon®

Makrolon® VR sheet

Impact Resistance*



*Instrumented Impact per ASTM D 3763,
sample thickness 0.125" nominal

Distributed by:



Piedmont Plastics®
where solutions take shape

Toll Free: 1.800.277.7898

www.piedmontplastics.com



The manner in which you use and the purpose to which you put and utilize our products, technical assistance and information (whether verbal, written or by way of production evaluations), including any suggested formulations and recommendations, are beyond our control. Therefore, it is imperative that you test our products, technical assistance, information and recommendations to determine to your own satisfaction whether our products, technical assistance and information are suitable for your intended uses and applications. This application-specific analysis must at least include testing to determine suitability from a technical as well as health, safety, and environmental standpoint. Such testing has not necessarily been done by Covestro.

Unless we otherwise agree in writing, all products are sold strictly pursuant to the terms of our standard conditions of sale which are available upon request. All information and technical assistance is given without warranty or guarantee and is subject to change without notice. It is expressly understood and agreed that you assume and hereby expressly release us from all liability, in tort, contract or otherwise, incurred in connection with the use of our products, technical assistance, and information. Any statement or recommendation not contained herein is unauthorized and shall not bind us. Nothing herein shall be construed as a recommendation to use any product in conflict with any claim of any patent relative to any material or its use. No license is implied or in fact granted under the claims of any patent.

With respect to health, safety and environment precautions, the relevant Safety Data Sheets (SDS) and product labels must be observed prior to working with our products.