

Product Bulletin

Concept[®] 203 **FLEXIBLE GLOSS WHITE PVC** **PERMANENT ADHESIVE**

Concept[®] 203 is a 3-mil premium white gloss flexible calendared vinyl film coated with 200-5000 permanent acrylic pressure sensitive adhesive laminated to a 90# layflat liner. This film is designed to accept a variety of solvent-based inkjet and UV curable inks common to wide format digital printing systems. Adhesive 200-5000 produces permanent bond to a variety of common substrates used in the graphics industry. The 90# liner offers excellent product layflat in a variety of environmental conditions.

Applications Concept[®] 203 is designed for interior or exterior signage, decals, nameplates, and point-of-purchase displays.

Thickness Film 3.0 mils.
Adhesive .9 to 1.1 mils.
Liner 6.7 mils.
(Thickness variance +/- 10%)

Dimensional Stability Good.

Temperature Ranges Minimum application temperature is +40°F.
Service temperature is -40°F to +180°F.

Expected Exterior Exposure Up to 5 years.

Adhesion To stainless steel - 40 oz/in.
PSTC-101 Method A with 24 hr. dwell at 70°F and 50% relative humidity.
Typical values. Individual values may vary.
Test thoroughly for your specific use.

Water Resistance Good. Test if immersed.
Humidity Resistance Good.
Solvent Resistance Good

Storage Stability 6-month shelf life when stored at 70°F and 50% relative humidity.

Product Codes 203-30 (30" X 150' roll)
203-54 (54" X 150' roll)
203-54RW (54" X 150' roll, reverse wound/ notched core)
203-60 (60" X 150' roll)

Recommendations Completely evaporate inkjet solvents before application. Failure to do so may facilitate solvent penetration resulting in vinyl degradation.



***Manufacturer of Pressure Sensitive Films,
Traffic Graffice Floor Advertising Films,
Custom Coatings and Printing Inks.***

309 S. Union • P.O. Box 158 • Sparta, Michigan 49345 • (616) 887-7387 • (800)253-3664 • FAX (616)887-0537
Web Site: www.generalformulations.com • e-mail: gfiinfo@generalformulations.com

We believe the information on this product to be accurate. However, since we cannot anticipate or control the conditions under which this information or our products may be used, we cannot guarantee results obtained through their use. Tests of our products should be made by users to determine the suitability of these products for a specific purpose. The products are sold without warranty, either express or implied. The purchaser should refer to General Formulations, Inc's Price List for Terms and Conditions or Sale, Including Disclaimer of Warranties and Limitation of Liability.