

For applications requiring more detailed technical data, please contact our specialists.

Properties	Testing Method	Unit	Values	Values
Mechanical				
Apparent density*	DIN 53 479	g/cm ²	0.55	0.65
Tensile strength	DIN 53 455	N/mm ²	12	20
Elongation at tear	DIN 53 455	%	15	15
Flexural strength	DIN 53 452	N/mm ²	20	30
Compressive strength (range of elasticity)	DIN 53 421 (serving as a basis)	N/mm ²	>3.0	>3.0
Compressive stress at 30%	DIN 53 421 (serving as a basis)	N/mm ²	>6.5	>13
Modulus of elasticity	DIN 53 457 (similar to)	N/mm	850	1100
Impact strength	DIN 53 453	kJ/m ²	~ 15	~ 10
Shore hardness D	DIN 53 505		55	45

Thermal

Vicat softening temp.	DIN 53 460	°C	78	75
Vicat A Temp of deflection under load acc. To ISO 75 (HDT)	DIN 53 461	°C	68	60
Coefficient of linear thermal expansion (-30°C to +50°C)	DIN 53 752	mm/m °C	0.08	0.08
Thermal conductivity (0°C to +60°C)	DIN 52 616	W/mK	0.06	0.10
Thermal Resistance R — 0.5" thick	C518		.948	
Thermal Resistance R per Inch — 0.5" thick	C518		2.17	

Electrical

Surface resistance	DIN VDE 0303 T3		6 • 10 ¹⁴	> 1 • 10 ¹⁴
Volume resistivity	DIN VDE 0303 T3	Ω cm	>10 ¹⁶	4 • 10 ¹⁵
Dielectric constant E _d	DIN VDE 0303 T2	kV/mm	5.0	16
Dielectric constant E _r (at 1 kHz)	DIN 53 483 T2		1.6 ± 0.5	2.5
Dielectric dissipation factor tan (at kHz)	DIN 53 483 T2		0.012	0.016
Comparative figure of tracking	DIN IEC 112		CTI 600	CTI 600

For applications requiring more detailed technical data, please contact our specialists.

Properties	Testing Method	Unit	Values	Values
Other				
Fire behavior (UL 94 & UL 1975 re-testing in progress)	UL 94 (USA)	≥ 2 mm (3 - 6 mm colored)		VO
Water absorption after 7 days	DIN 53 495	%	<0.3	<0.3
Flame Spread Index (Re-testing in progress)				
Komatex — White	E84-03		45	
Komatex — Black	E84-03		10	
Komatex — Color	E84-03		15	
Smoke Developed Index (Re-testing in progress)				
Komatex — White	E84-03		850	
Komatex — Black	E84-03		400	
Komatex — Color	E84-03		350	
Allowable for contact with foodstuff				No

*These are standard values that apply to an average density. Small variations depending on the sheet thickness are possible. Technical specifications are subject to change.

Distributed by:



Toll Free: 1.800.277.7898

www.piedmontplastics.com