

SCS1700 Sanitary

silicone sealant

Product Description

SCS1700 silicone sealant is a one-component, acetoxycure silicone containing a fungicide that is supplied as a paste and upon cure, produces a durable, formed-in-place silicone rubber seal that is mildew and mold resistant. SCS1700 is an excellent candidate to consider the prevention of mildew formation around fixtures in areas such as locker rooms, swimming pool facilities and lavatories.

Typical Performance Properties

Performance

- **Silicone Durability** - Cured silicone provides excellent long-term resistance to natural weathering, humidity and high & low temperatures with negligible change in elasticity.
- **Mildew Resistant** - Contains a fungicide that enables the sealant to resist both mold and mildew even when exposed to prolonged hot and humid environments.
- **±25% Movement Capacity** - Can accommodate 25% movement in both extension and compression and has excellent recovery after cycling.

Application

- **Fast Cure Time** - Tack free in 30 minutes and full cure of many common bead sizes in 24-48 hrs.
- **Adhesion** - Primerless adhesion to many substrates and finishes including: glass, ceramic, porcelain, tiles, stainless steel, numerous plastics, glazed surfaces, imitation marble, aluminum, and many composite materials. Some finishes or substrates may require a primer.
- **Good Workability** - Temperature stable paste which is easily gunned and tooled under hot and cold conditions.
- **Thermal Stability** - Once cured, the material properties remain fully elastic over a range of -55°F (-48°C) to 400°F (204°C).
- **Low Sag or Slump** - Useful for application to horizontal, vertical or overhead surfaces.

GE is a registered trademark of General Electric Company and is under license by Momentive Performance Materials Inc. Momentive Performance Materials provides versatile materials as the starting point for its creative approach to ideas that help enable new developments across hundreds of industrial and consumer applications. We are helping customers solve product, process, and performance problems; our silanes, fluids, elastomers, sealants, resins, adhesives, urethane additives, and other specialty products are delivering innovation in everything from car engines to biomedical devices. From helping to develop safer tires and keeping electronics cooler, to improving the feel of lipstick and ensuring the reliability of adhesives, our technologies and enabling solutions are at the frontline of innovation.



Licensed
Products

Distributed by:



Piedmont Plastics®
where solutions take shape

Toll Free: 1.800.277.7898

www.piedmontplastics.com

SCS1700 Sanitary silicone sealant

Basic Uses

SCS1700 is a candidate to consider:

- For use as a seal around bathtubs, shower stalls, wall fixtures, sinks, and other bathroom fixtures including countertops, soap fixtures, air dryers and drains.
- For grouting and bedding some ceramic tiles.
- In interior and exterior applications where areas are prone to mold and mildew formation.

Customer Evaluation

Customers must evaluate Momentive Performance Materials (MPM) products and make their own determination as to fitness of use in their particular applications.

Packaging

SCS1700 is available in 10.1 fl. oz. (299 ml) plastic caulking cartridges with removable nozzles. Removable nozzles are easily transferred between cartridges for consistent bead size without having to re-cut each nozzle. Plastic cartridges are packaged as 24 units in cardboard boxes and are dispensed using a single component hand or air-pressured caulking gun.

Colors

SCS1700 is available in 2 standard colors plus translucent.

Grade	Color
SCS1701	Translucent
SCS1702	White
SCS1705	Almond

Limitations

SCS1700 is not recommended:

- For use underwater or in other applications where the product will be in continuous contact with water.
- For use in food contact applications.
- When painting of the cured sealant is desired unless appropriate specialized paint products are used such as GE SEC2400 SilShield*.
- For use on aquariums as leaching of the fungicide can occur.
- For use on surfaces with special coatings, such as mirrors, without testing and approval of the manufacturer of the article.

SCS1700 should not be applied or used:

- Under exceedingly hot or cold conditions (see Sealant Typical Properties table).
- On wet, damp, frozen or contaminated surfaces.
- On excessively basic or acidic substrates.
- On concrete, marble, limestone, lead or lead coated surfaces.
- In designs or applications where the silicone is encapsulated and without access to atmospheric moisture needed to cure.

Technical Services

Additional technical information, literature, laboratory testing and application engineering may be available upon request from MPM. Any technical advice furnished by MPM or any representative of MPM concerning any use or application of any MPM product is believed to be reliable but MPM makes no warranty, expressed or implied, of suitability for use in any application for which such advice is furnished.

Typical Properties – Supplied

Property	Value ⁽¹⁾	Test Method
Consistency	Paste	
Polymer	100% silicone	
VOC	20 g/l	WPSTM C1454
Work Life (tooling time)	5-10 minutes	
Tack Free Time (@ 72°F (22°C), 50% RH)	30-45 minutes	ASTM C679
Sag/Slump	0.1"	ASTM D2202

Typical Properties – Cured

Property	Value ⁽¹⁾	Test Method
Hardness, Durometer (Type A Indentor)	30	ASTM D2240
Ultimate Tensile Strength	292 psi (2.0 MPa)	ASTM D412
Ultimate Elongation	373%	ASTM D412
Peel Strength (average) (21-day cure @ 75°F (24°C) 50% RH)	30.4 pli (5.3 kN/m)	ASTM C794
Joint Movement Capability	±25%	ASTM C719
Service Temperature Range (after cure)	-55°F to +350°F (-48°C to 177°C)	
Application Temperature Range	+40°F to +122°F (4°C to 50°C)	
Weathering and U.V. Resistance	Excellent	GE 20 yr. study
Cure Time (1/4" or 6 mm deep section) @ 75°F (24°C) 50% RH	2-3 days	

(1) Average value. Actual value may vary.

Applicable Standards

SCS1700 meets or exceeds the requirements of the following specifications:

American Society for Testing & Materials International

- ASTM C 920 Standard Specification for Elastomeric Joint Sealants; Type S, Grade NS, Class 25, Use A, G, O, NT

U.S. Federal Specifications: (cancelled Sept. 1996)

- TT-S-001543A Sealing Compound: Silicone Rubber Base (for Caulking, Sealing & Glazing in Buildings and Other Structures)
- TT-S-00230C Sealing Compound: Elastomeric Type, Single Component (for Caulking, Sealing & Glazing in Buildings and Other Structures)

Canadian General Standards Board (inactive)

- CCGSB-19.13-M87 Sealing Compound, One-Component, Elastomeric, Chemical Curing
- CGSB-19.22-M89 Mildew-Resistant Sealing Compound for Tubs and Tiles

SCS1700 Sanitary silicone sealant

Installation

Sealants may not adhere or maintain long-term adhesion to substrates if the surface is not prepared and cleaned properly before sealant application. In all cases the applicator must confirm the acceptability of each sealant-substrate combination with a site adhesion test prior to proceeding with project installation. A GE sealant primer may be selected to enhance sealant bonding on some difficult to adhere to substrates. MPM can provide information and suggestions to user upon request.

Surface Preparation

Glass, Metals Paints, Smooth Surfaces, etc.

- Smooth surfaces can be wiped clean using a rag dampened with a cleaning solvent (Isopropyl Alcohol is typically useful). Proceed by cleaning the surfaces using a rag wetted with solvent and immediately use a second clean rag to wipe the wet solvent from the surface before it evaporates. Repeat this procedure as necessary until no contaminants are visible on the second cleaning rag.
- Rough surfaces such as concrete, brick and masonry can be cleaned by wire brush, mechanical abrading, grinding or a combination of these methods to provide a stable clean surface for sealant application. Secondly, follow this with an air blow or brush (soft-bristled) to remove dust.
- All surfaces that are to receive sealant must be clean, dry and free of contaminants (such as moisture/frost, oils, concrete form release agents, old sealants, asphalt and other surface treatments, etc.) to allow for optimal adhesion.

Masking

The use of masking tape is recommended where appropriate to ensure a neat job and to protect adjoining surfaces from over-application of sealant. Masking tape should be removed immediately after tooling the sealant and before the sealant begins to skin over (tooling time).

Storage Conditions

SCS1700 should be stored in the original unopened container at 80°F (27°C) or lower.

Patent Status

Nothing contained herein shall be construed to imply the nonexistence of any relevant patents or to constitute the permission, inducement or recommendation to practice any invention covered by any patent, without authority from the owner of the patent.

Product Safety, Handling and Storage

Customers considering the use of this product should review the latest Material Safety Data Sheet and label for product safety information, handling instructions, personal protective equipment if necessary, and any special storage conditions required. Material Safety Data Sheets are available at www.ge.com/silicones or, upon request, from any MPM representative. Use of other materials in conjunction with GE sealants products (for example, primers) may require additional precautions. Please review and follow the safety information provided by the manufacturer of such other materials.

Emergency Service

Momentive Performance Materials maintains an around-the-clock emergency service for its products.

<u>Location</u>	<u>Emergency Service Provider</u>	<u>Emergency Contact Number</u>
Mainland U.S., Puerto Rico	CHEMTREC	1-800-424-9300
Alaska, Hawaii	CHEMTREC	1-800-424-9300
Canada	CHEMTREC	1-800-424-9300
Europe, Israel	NCEC	+44 (0) 1235239670
Middle East	NCEC	+44 (0) 1235239671
Asia Pacific (except China)	NCEC	+44 (0) 1235239670
China	NCEC	+86-10-5100-3039
Latin America (except Brazil)	NCEC	+44 (0) 1235239670
Brazil	SOS Cotec	08000111767 or 08007071767
All other locations world wide	NCEC	+44 (0) 1235239670
At sea	Radio U.S. Coast Guard in U.S. waters NCEC in International waters	+44 (0) 1235239670

For Health related calls, contact Momentive Performance Materials at +1-518-233-2500 (English only).

DO NOT WAIT. Phone if in doubt. You will be referred to a specialist for advice.

SCS1700 Sanitary silicone sealant

THE MATERIALS, PRODUCTS AND SERVICES OF MOMENTIVE PERFORMANCE MATERIALS INC., MOMENTIVE PERFORMANCE MATERIALS USA INC., MOMENTIVE PERFORMANCE MATERIALS ASIA PACIFIC PTE. LTD., MOMENTIVE PERFORMANCE MATERIALS WORLDWIDE INC., MOMENTIVE PERFORMANCE MATERIALS GmbH, THEIR SUBSIDIARIES AND AFFILIATES DOING BUSINESS IN LOCAL JURISDICTIONS (collectively "SUPPLIERS"), ARE SOLD BY THE RESPECTIVE LEGAL ENTITY OF THE SUPPLIER SUBJECT TO SUPPLIERS' STANDARD CONDITIONS OF SALE, WHICH ARE INCLUDED IN THE APPLICABLE DISTRIBUTOR OR OTHER SALES AGREEMENT, PRINTED ON THE BACK OF ORDER ACKNOWLEDGMENTS AND INVOICES, AND AVAILABLE UPON REQUEST. ALTHOUGH ANY INFORMATION, RECOMMENDATIONS, OR ADVICE CONTAINED HEREIN IS GIVEN IN GOOD FAITH, SUPPLIERS MAKE NO WARRANTY OR GUARANTEE, EXPRESS OR IMPLIED, (i) THAT THE RESULTS DESCRIBED HEREIN WILL BE OBTAINED UNDER END-USE CONDITIONS, OR (ii) AS TO THE EFFECTIVENESS OR SAFETY OF ANY DESIGN INCORPORATING SUPPLIERS' PRODUCTS, MATERIALS, SERVICES, RECOMMENDATIONS OR ADVICE. AFOREMENTIONED EXCLUSIONS OR LIMITATION OF LIABILITY ARE NOT APPLICABLE TO THE EXTENT THAT THE END-USE CONDITIONS AND/OR INCORPORATION CONDITIONS CORRESPOND TO THE RECOMMENDED CONDITIONS OF USE AND/OR OF INCORPORATION AS DESCRIBED BY SUPPLIER IN ITS PRODUCT DATA SHEET AND/OR PRODUCT SPECIFICATIONS. EXCEPT AS PROVIDED IN SUPPLIERS' STANDARD CONDITIONS OF SALE, SUPPLIERS AND THEIR REPRESENTATIVES SHALL IN NO EVENT BE RESPONSIBLE FOR ANY LOSS RESULTING FROM ANY USE OF ITS MATERIALS, PRODUCTS OR SERVICES DESCRIBED HEREIN.

Each user bears full responsibility for making its own determination as to the suitability of Suppliers' materials, services, recommendations, or advice for its own particular use. Each user must identify and perform all tests and analyses necessary to assure that its finished parts incorporating Suppliers' products, materials, or services will be safe and suitable for use under end-use conditions. Nothing in this or any other document, nor any oral recommendation or advice, shall be deemed to alter, vary, supersede, or waive any provision of Suppliers' Standard Conditions of Sale or this Disclaimer, unless any such modification is specifically agreed to in a writing signed by Suppliers. No statement contained herein concerning a possible or suggested use of any material, product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right of Suppliers or any of its subsidiaries or affiliates covering such use or design, or as a recommendation for the use of such material, product, service or design in the infringement of any patent or other intellectual property right.

*SilShield is a trademark of Momentive Performance Materials Inc.
GE is a registered trademark of General Electric.
Momentive and the Momentive logo are trademarks of Momentive Performance Materials Holdings Inc.
Copyright 2010-2013 Momentive Performance Materials Inc. All rights reserved.

161-011-30E-GL
CDS: DataSCS1700 (05/13)