

LubX® CV

Product characteristics

- Excellent sliding properties even at higher load
- Outstanding dry running characteristics
- FDA

Typical field of application

- Conveyor Technology
- Material Handling
- Automation

	ASTM Test method	Unit	Value
Physical Properties			
Specific Gravity	D792	g/cm ³	0.94
Water Absorption	D570	%	≤ 0.01
Mechanical Properties			
Hardness	D785	Shore D	60
Elongation at Break	D638	%	≥250
Izod Impact, Notched	D256	ft-lb/in	No Break
Sliding properties: partner POM (0,5m/s – 0,5MPa)	REP – Tribology – Test	-	0.13
Thermal properties			
CTE, linear	D696	1/K	1.0 x 10 ⁻⁴
Melting Point	D3418	°F	275
Maximum Service Temperature, Air	-	°F	180
Deflection Temperature at 1.8Mpa (264psi)	D648	°F	108
Flammability, UL94	-	1/8 inch	HB
Electrical properties			
Surface resistivity	D257	Ohm/cm	≥10 ¹⁴
Compliance Properties			
FDA	-	-	Yes
NSF	-	-	No
USDA	-	-	Yes

The data stated above are average values ascertained by statistical tests on a regular basis. The data above are provided purely for information and shall not be regarded as binding unless expressly agreed in a contract of sale.

Distributed by:



Toll Free: 1.800.277.7898
www.piedmontplastics.com

Status: April 12, 2016

