

## SUSTAPVDF (Kynar 740)

	ASTM Test method	Unit	Value
<b>Physical Properties</b>			
Specific Gravity	D792	g/cm <sup>3</sup>	1.78
Water Absorption 24 hours	D570	%	0.03
Water Absorption Saturation	D570	%	0.05
Dissipation Factor	D150	1 MHz	0.06
<b>Mechanical Properties</b>			
Hardness	D785	Shore D	D77
Rockwell Hardness	D785	M	M75
Rockwell Hardness	D785	R	R84
Tensile Strength at yield 73 °F	D638	psi	7,000
Tensile Modulus	D638	psi	250,000
Elongation at Break	D638	%	100
Flexural Strength	D790	psi	8,000
Flexural Modulus	D790	psi	290,000
Compressive Strength	D695	psi	10,500
Shear Strength	D732	psi	-
Izod Impact, Notched	D256	ft-lb/in	3
Coefficient of Friction, Dynamic	-	-	0.58
<b>Thermal properties</b>			
CTE, linear	D696	in/in/°F	6.6x10 <sup>-5</sup>
Melting Point	D3418	°F	335
Continuous Use	-	°F	300
Thermal Conductivity	-	in/hr/ft <sup>2</sup> /F°	0.75
Deflection Temperature at 1.8Mpa (66psi)	D648	°F	270
Deflection Temperature at 1.8Mpa (264psi)	D648	°F	230
Flammability, UL94	-	1/8 inch	V-0
<b>Electrical properties</b>			
Dielectric constant	D150	-	8.5
Surface resistivity	D257	Ohm/cm	10 <sup>14</sup>
Dielectric strength	D149	V/mil	1600
<b>Compliance Properties</b>			
FDA	-	-	Yes

The data stated above are average values ascertained by statistical tests on a regular basis. The data above are provided purely for information and shall not be regarded as binding unless expressly agreed in a contract of sale.

Röchling Engineering Plastics  
903 Gastonia Technology Parkway, Dallas, NC 28034, USA - Tel.:704 922 7814 – info@roechling-plastics.us – www.roechling-plastics.us