

SUSTARIN® H (Acetal Homopolymer “Delrin”)

	ASTM Test method	Unit	Value
Physical Properties			
Specific Gravity	D792	g/cm ³	1.42
Water Absorption 24 hours	D570	%	0.2
Water Absorption Saturation	D570	%	0.7
Dissipation Factor	D150	1 MHz	-
Mechanical Properties			
Hardness	D785	Shore D	D78
Rockwell Hardness	D785	M	M85
Rockwell Hardness	D785	R	R115
Tensile Strength at yield 73 °F	D638	psi	15,000
Tensile Modulus	D638	psi	420,000
Elongation at Break	D638	%	40
Flexural Strength	D790	psi	12,000
Flexural Modulus	D790	psi	400,000
Compressive Strength	D695	psi	16,000
Shear Strength	D732	psi	9000
Izod Impact, Notched	D256	ft-lb/in	1.2
Coefficient of Friction, Dynamic	-	-	0.12
Thermal properties			
CTE, linear	D696	in/in/°F	6.7x10 ⁻⁵
Melting Point	D3418	°F	347
Continuous Use	-	°F	185
Thermal Conductivity	-	in/hr/ft ² /F°	2
Deflection Temperature at 1.8Mpa (66psi)	D648	°F	290
Deflection Temperature at 1.8Mpa (264psi)	D648	°F	242
Flammability, UL94	-	1/8 inch	HB
Electrical properties			
Dielectric constant	D150	-	3.1
Surface resistivity	D257	Ohm/cm	10 ¹⁶
Dielectric strength	D149	V/mil	400
Compliance Properties			
FDA	-	-	Yes

The data stated above are average values ascertained by statistical tests on a regular basis. The data above are provided purely for information and shall not be regarded as binding unless expressly agreed in a contract of sale.

Röchling Engineering Plastics
903 Gastonia Technology Parkway, Dallas, NC 28034, USA - Tel.:704 922 7814 – info@roechling-plastics.us – www.roechling-plastics.us