



Quintium™ Q20 Transparent Armor


Quintium™ is a two-part 100% solids castable system. Castings are clear and can be made to optical specifications. Quintium contains a UV stabilizer package and absorbs UV radiation up through 400 nm. It can be formulated with fire retardant additives, can be tinted and has excellent heat and solvent resistance. Quintium is highly impact resistant and has a minimum V50 rating at 1139 fps. Typical “stacked” arrays may be used to improve the ballistic profile of Quintium. Quintium can be cast in various thicknesses and numerous mold configurations.

Key properties include:

- Unrivaled impact resistance and kinetic energy absorption
- Exceptional multi-hit performance
- Great optical clarity
- Significantly reduced weight: approximately ½ of ballistic glass
- Unlike most other ballistic-resistant polymers, it is resistant to chemical solvents and aromatic hydrocarbons (e.g. gasoline)
- No charring when burning

Applications

- Bullet-resistant windows for vehicles & buildings
- Safety goggles or eye shields
- Hurricane windows
- Forced entry resistant glazing
- Transparent structures & components
- Blast-resistant transparencies
- Personal armor shielding



*Instrumented Impact per ASTM D3763, sample thickness 0.125" nominal

Distributed by:



Piedmont Plastics®
where solutions take shape


Toll Free: 1.800.277.7898
www.piedmontplastics.com



Typical Properties*

Property	Test Method	Units	Values
Physical			
Specific Gravity	ASTM D 792	--	1.11
Hardness	ASTM D 2240	Shore D	80-82
HDT	ASTM D 648	F	300-320
Stress Craze Resistance (IPA)	ASTM F 791	psi	>7,000
Mass / Area	--	lb/ft ²	0.69
Mechanical			
Tensile Strength	ASTM D 412	psi	8,000
Elongation	ASTM D 412	%	42
Flexural Modulus	ASTM D 790	psi	194,000
Izod Impact Strength, Unnotched @ 0.125"	ASTM D 4812	ft-lbs/in	54 (no failure)
Instrumented impact @ 0.125"	ASTM D 3763	ft-lbs	>65
Optical			
Refractive Index	ASMT D 542	--	1.538
Light Transmission, Clear @ 0.118"	ASTM D 1003	%	90
Abbe Value	ASMT D 542	--	42-45
Haze	ASTM D 1003	%	0.33
Ballistics			
Curved Face Shield	NIJ IIIA	Projectile 9mm 124gr. FMJ	Meets the criteria

**Typical properties are not intended for specification purposes.*



Warning & Limitations

The information and data contained herein do not constitute sales specifications. No liability, warranty or guarantee of product performance is created by this document. It is the Buyer's responsibility to determine whether Hanson products are appropriate for Buyer's use and to ensure that Buyer's workplace and disposal practices are in compliance with applicable laws and regulations. No freedom from any patents or other industrial or intellectual property rights is granted or to be inferred.



Distributed by:



Piedmont Plastics[®]
where solutions take shape

Toll Free: 1.800.277.7898

www.piedmontplastics.com